

### Description

UHVO-20114 is a Chlorinated Polyester diluted in 40% TMPTA for use in UV and EB curing applications.

### Characteristics

- Fast cure
- Low odour
- Very good adhesion to metal and film
- Excellent pigment wetting properties
- Excellent lithographic properties

### Suggested Application

- Printing Inks
- Overprint Varnishes
- UV Offset

### Typical Properties

Acid value [mg KOH/g]	8 - 12
Appearance	clear liquid
Colour, Gardner	≤ 3
Viscosity @ 20 °C, Physica, D = 5/s [Pa·s]	485 - 535

### Storage

The resin should be stored in a cool, dry place and should not be exposed to direct sunlight. Typical storage temperatures should be between 15 - 30 °C. Do not store this product under an oxygen-free atmosphere, as the inhibitor requires oxygen to work.

### Shelf Life

The product has a shelf life of at least 12 months from the date of manufacture.

### Safety

When handling this product, please work according to the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.