



## Gecko® Frontal Eco

Solvent based printing inks for flexible packaging  
**Surface printing**

### Description

A full colour range of highly pigmented plurisolvent nitrocellulose printing inks designed for surface printed applications on flexible films, supplied as finished products or for use as mono pigmented concentrates and system additive.

### Printing Process

Flexographic and gravure printing.

### Applications

Surface printing.








Suitable for food and beverage flexible packaging.

**Substrates:** LDPE, HDPE, Coex OPP\*, Paper, NC-tr. Aluminium.

\* For printing on polypropylene the addition of Adhesion Promoter (70GH278345 – Amount 3%) might be necessary.

**Minimum surface tension:** LDPE, HDPE, Coex OPP: 38 mN/m (mN/m = dynes/cm)

### Properties

Adhesion		Water resistance	
Rub resistance		Deep freeze resistance	
Scratch resistance		Vegetable oil resistance	
Heat resistance	160° - 170° C	C.O.F. (dynamic, range)	0.20 – 0.30
Gloss		Light fastness	3 – 8 (*)

■ = positive rating point on a scale from zero to max. Ten points for highest value / best suitability. (\*) for Light Fastness: 3 = half tone, 8 = full tone, but for a specific and correct light fastness to take as a reference the values indicated for each C.I. in the TDS Annex I (11.P.018).

**Note:** All technical properties are a guideline only and depend on pigment choice and final application. For details about exact test methods, which are the basis for info about fastness properties given above, please refer to the general test method overview.

## Auxiliaries

<b>Metallics:</b>	A full range of Gecko imitation gold and silver inks is available.
<b>Additives:</b>	A full range of additives is available to modify the performances of Gecko Frontal Eco.
<b>Process Inks:</b>	A range of slow drying flexo half-tone process colours is available (GFE raster).

## Printing viscosity

Diluents	Flexographic Printing 20 – 25 s DIN 4	%	Gravure Printing 13 – 15 s DIN 4	%
<b>Slow</b>	n-Propanol/n-Propyl Acetate	90:10 to 70:30	Ethanol/n-Propyl Acetate	50:50 to 75:25
<b>Standard</b>	Ethanol/Ethyl Acetate	90:10 to 70:30	Ethanol/Ethyl Acetate	50:50 to 30:70
<b>Fast</b>			Ethyl Acetate	100
<b>Retarder</b>	Ethoxy Propanol	10% max	Ethoxy Propanol	5% max

## Gecko Frontal Eco inks from Concentrates

With mixing stations or other equipment, it is possible to produce ready-made Inks of the Gecko Frontal Eco Series using the concentrates of the Gecko Base Series and the appropriate System Additive Gecko Frontal Eco (00GE242057).

For this operation, it is required a mixing ratio of:

- 20% of System Additive GFE (00GE242057)
- 60% of Gecko Base products (Colour Concentrates and NC varnish 00GB274057).
- 20% of free solvent

No warranties can be given if products from other manufacturers are mixed with **hubergroup** products.

## Instructions for the use of printing inks for the production of primary food packaging

For information on the use of printing inks, varnishes and additives for the manufacture of food packaging please refer to the respective „**Statement of Composition**". This information is provided to allow the calculation of possible levels of migration of evaluated substances in a worst case situation.

Migration tests at **hubergroup** laboratories with printed samples made from commercially available OPP film (film thickness: 35 u. printed wet ink: 6 g/m<sup>2</sup>, with 95 % ethanol as the food simulant) and PE film (film thickness: 50 u, printed wet ink: 6 g/m<sup>2</sup>, with 95 % ethanol as the food simulant) showed no migration of substances above legal limits. Based on the results of these migration tests, we expect that the printed inks enable the final printed products to comply with the legal requirements for packaging for all kinds of foodstuff.

The manufacturer of the finished article and the filler have the legal responsibility to prove by appropriate migration testing that it is fit for its intended purpose.

In order to maintain low residual solvents concentration in the printed film, the printer must ensure sufficient drying of the product, especially when retarders have been added. Residual solvent content must be regularly monitored.

The products must not be used in the manufacture of packaging where the printed ink layer is intended to come into contact with foodstuff (direct food contact).

There are restrictions for the use of printing inks for applications where temperatures above 100 °C for extended periods of time are applied. For details, please see document "Food Packaging Inks for High Temperature Applications".

## **Health & Safety**

The material safety data sheets contain all relevant information for the generation of appropriate internal plant instructions. The user is responsible for all local legislation requirements.

## **Ink Handling**

Please refer to General Guidelines for handling inks for flexible packaging.

## **Storage Conditions**

Store the material in the original packaging at a temperature not below 5°C and not in direct contact with sunlight.

Contact addresses for advice and further information can be found under [www.hubergroup.com](http://www.hubergroup.com)

Due to the many variables in materias for printing, design construction, processing conditions and test criteria, this Technical Data Sheet can only be of an advisory nature. Our data reflect the latest state of our knowledge and are based on the characteristics established in the laboratory and on practical experience. Because there are many factors under the control of the user which may affect processing or application/use, it is necessary for the user to carry out appropriate tests to determine whether the product(s) is technically and safely suitable for the particular purpose, prior to use. hubergroup disclaims any liability for applications for which this ink series is not foreseen. No warranties of any kind, either expressed or implied, are made regarding the products here described. The English version is the master document, on which to refer for any translations.